TECHNICAL DATA SHEET							
Manufacturer Name	SHEETSOL PVT. LTD,						
	Raipur, Chhattisgarh, India-492 001.						
Product Details							
Product Name	Sheetsol POE						
Product Type	POE Encapsulant - Polymeric Material						
Test Items	POE 360						
Test / Parameter	Test Method	unit	Customer specification				
Thickness	-	mm	0.5080mm ± 10%				
Density	ASTMD 792	g/cm ³	0.88				
Thermal Shrinkage	160 °C on glass plate for 5	%	≤3				
Tanaila Chuanath		min.					
Tensile Strength	ASTM D638 MPa		12 ± 3				
Elongation at break Peel strength	ASTM D 638 % ASTM D903 N/cm		≥ 500 ≥70				
(Glass/Film)	ASTIVI D903 N/cm		270				
Peel strength (TPT/Film)	ASTM D903 N/cm		≥70				
Specific Heat	ISO22007 PART 2	j/g. k	1.96-2.01				
Optical Transmission	ASTM E424 SPECTROPHOTO	%	≥91				
after curing	METER						
UV Cut Off Wavelength	ASTM E424 SPECTROPHOTO METER	nm	360				
Yellow Index	ΔΥΙ	-	≤2				
Gel Content	ASTM D2765-01	%	≥50				
Refractive Index	ISO489		1.49				
Volume Resistivity	ASTM D257	Ohm.cm	1.0 x 10 ¹⁶				
Water absorption	ISO 62-200805	%	0.10				
Lamination Parameters							
Evacuation Time	-	Minutes	4 to 5				
Lamination Time	-	Minutes	6 to 8				
Temperature	-	°C	145 to 160				
Storage and Packing Details							
Storage Conditions	Store in sealed packing at temperature < 28°C & humidity < 60%						
Shelf Life	Recommended to use before 6 months from the date of manufacture						
Declaration							
	nity (DoC) Certifies that a con st faculty using approved met	•	luct has been tested by an ke sure it is fully operational and				
Report No.02	SS\LAB\220601-01						
Place: Raipur	Raipur						
Date: 21/07/2023	21 July, 2023		Sign and Stamp of Authorized Person				
			Girish Suthar : +91-9825244653				